

FIREBREAK™362



**TIME TESTED
FORESTRY
PROTECTION**

MADE WITH TRUSTED DUPONT® NOMEX® FIBERS

Woven for over three decades with long-lasting Nomex® fiber.

THE FORESTRY STANDARD

Widely recognized as the unofficial uniform for Wildland firefighters.

UNIQUELY WOVEN FOR STRENGTH

Basket weave construction allows for strength through long hours and rugged terrain.

FIREBREAK™ 362

| TECHNICAL DATA* | FIREBREAK™ 362 |
|-----------------|-------------------------------------|
| Nominal Weight | 5.8 osy (197 gsm) |
| Construction | Woven |
| Color | Yellow |
| Fiber Content | Meta-Aramid, Para-Aramid, Anti-Stat |
| Finish | Shelltite™ |
| Certification | NFPA 1977 |

Flame Resistance

| | | |
|---|-------------|----------------------|
| Vertical Flame ASTM 6413, NFPA 1977 | After flame | < 2.0 sec |
| | Char length | < 4.0 in (100 mm) |
| Thermal Shrinkage NFPA 1977 | Initial | < 2.5% |
| Radiant Protective Performance NFPA 1977 | | 8.5 W/m ² |

Physical Testing

| | |
|--|-----------------------------|
| Tensile Strength ASTM D5034 (Warp x Fill) | 200 x 130 lbf (890 x 578 N) |
| Elmendorf Tear ASTM D1424, (Wrap x Fill) | 25 x 20 lbf (111 x 89 N) |
| Dimensional Stability AATCC 135 | < 4.0% |

Comfort

| | |
|----------------------------------|--|
| Air Permeability ASTM D737-96 | 70 ft ³ /ft ² /min |
| Total Heat Loss NFPA 1977 | 684 watts/m ² |

* Appearance is dependent on shade of fabric.

AVAILABLE COLORS

Yellow



TenCate Protective Fabrics
is certified according:



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.